

ZINTL™

Technical Data Sheet

Properties	Units	Values
Alloy		6063
Temper		T5
Standard Thickness	mm	1.4mm to 2.2mm
Painted Weight	kg/m ²	0.642kg/m to 1.575kg/m
Raw Density	kg/m ³	2700
Young's Modulus (E)	GPa	68.3
Tensile Strength (25°C)	MPa	220
Yield Strength (25°C)	MPa	180
Shear Strength	MPa	117
Fatigue Strength	MPa	69
Elastic Modulus	MPa	69
0.2% Proof Stress	MPa	>170
Elongation	%	12
Linear Thermal Expansion		2.4mm/m at 100°C temperature difference
Melting Range	°C	630-660
Electrical Conductivity (Equal Volume)	MS/m	32
Electrical Conductivity (Equal Mass)	MS/m	105
Thermal Conductivity	W/m.K	201-218
Sound Absorption Factor	NCR	0.05
Sound Reflection	%	95

A.B.N. 75 104 808 853 | www.hvgfacades.com.au | P 1300 881 712

SYDNEY
29 Henderson Street
Turrella NSW 2205

MELBOURNE
25 West Park Drive
Derrimut VIC 3030

BRISBANE
128 Mica Street
Carole Park QLD 4300

PERTH
72 Bushland Ridge
Bibra Lake WA 6163

ADELAIDE
57 Barnes Avenue
Marleston SA 5033

ALUCOBOND®

MondoClad

**SWISS
pearl®**

ZINTL

SIDERISE®

TRESPA®

TERREAL