



MondoClad® Technical Data Sheet

Properties	Units	Values
Alloy		5052
Temper		H32
Standard Thickness	mm	3
Painted Weight	kg/m ²	8.31
Paint Thickness	micron (nom)	>30
Raw Density	kg/m ³	2680
Indicative Minimum Radius	mm	4.5
Tensile Strength	MPa	215-265
0.2% Proof Stress	MPa	>160
Elongation	%	7
Linear Thermal Expansion		2.4mm/m at 100°C temperature difference
Melting Range	°C	607-650
Modulus of Elasticity - Tension	GPa	69.3 @ 20°C
Modulus of Elasticity - Torsion	GPa	25.9 @ 20°C
Modulus of Elasticity - Compression	GPa	70.7 @ 20°C
Thermal Conductivity	W/m.K	138 @ 25°C
R Value	m ² •K/W	0.429
Electrical Resistivity	micro-ohm.m	70.7 @ 20°C
Electrical Conductivity - Equal Volume	MS/m	20 @ 20°C
Electrical Conductivity - Equal Weight	MS/m	67 @ 20°C
Sound Absorption Factor	NCR	0.05
Sound Reflection	%	95

Note: The MondoClad PVDF coating is produced in accordance with the American Architectural Manufacturers Association Standard AAMA 2605-11 that includes Specification, Performance Requirements and Test Procedures.

Version: 1.6.21

HVG Facades Pty Ltd | ACN: 634 557 270 | hvgfacades.com.au | 1300 881 712

SYDNEY
29 Henderson Street
Turrella NSW 2205

MELBOURNE
25 West Park Drive
Derrimut VIC 3026

BRISBANE
128 Mica Street
Carole Park QLD 4300

PERTH
72 Bushland Ridge
Bibra Lake WA 6163

ADELAIDE
57 Barnes Avenue
Marleston SA 5033